

Technical Data Sheet

Type: PEARLSTICK™ 5715 F2 TPU is an aromatic polyester-based thermoplastic polyurethane.

Main Application: Solution coating

Physical Properties	Value (Metric)	Units	Test Method
Specific Gravity	1.20	g/cm ³	ISO 2781
Shore Hardness	A/1:95 – D/1:49	Shore A/D	ISO 868
Mechanical			
Tensile Strength	18	MPa	ISO 527-2/5A/200
Modulus			
- 50% Elongation	4	MPa	ISO 527-2/5A/200
- 100% Elongation	4	MPa	ISO 527-2/5A/200
Ultimate Elongation	350	%	ISO 527-2/5A/200
Brookfield Viscosity			
- 20% T.S. in MEK	40-110	cps	
Tear Strength Unnicked	75	kN/m	ISO 34-1B
Thermal			
Kofler Melting Point	80	° C	LZMM-RD01-70
Solubility			
Methylethylketone (MEK)	Soluble		
Dimethylformamide (DMF)	Soluble		
Tetrahydrofuran	Soluble		
Ethylacetate	Swelling		
Cyclohexanone	Soluble		

- ¹Prior to testing samples were conditioned at 23° C for 48 hours.
- Based on solution cast films of 30-50 microns thickness.
- Listed values are "typical (average) values" and should/can not be applied for specification purposes.

Supply Form and Standard Packaging

PEARLSTICK™ 5715 F2 TPU is supplied in pellet form and packaged in 25Kg bags.

STORAGE

PEARLSTICK™ 5715 F2 must be stored in a cool (19° C) and environment prior to being processed. Standard practice of consuming resin on first-in first-out basis should be employed.

For further information refer to Lubrizol Advanced Materials processing guides.

The Lubrizol Corporation ("Lubrizol") hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.