

Technical Data Sheet

Type: ESTANE® ZHF 95AP7 NAT 01 is a 95A aromatic Thermoplastic Polyurethane (TPU).

Features: Zero Halogen, Flame Retardant compound with low smoke and high Limiting Oxygen Index.

Application: Extrusion

Physical Properties	Value (Metric)	Unit	Test Method
Hardness	A/1: 95	Shore A	ISO 868
Specific Gravity	1.39	g/cm ³	ISO 1183
Tensile Strength	22	MPa	ISO 527-200
Ultimate Elongation	280	%	ISO 527-200
Tensile Stress at:			
- 50% Elongation	13	MPa	ISO 527-200
- 100% Elongation	14	MPa	ISO 527-200
Abrasion Loss	120	mm ³	ISO 4649-A
Tear Strength nicked	95	kN/m	ISO 34-1B

- Based on extruded strips
- Prior to testing samples were conditioned at 23°C for 48 hours
- Listed values are "typical (average) values" and should/cannot be applied for specification purposes.

Application Specific Properties	Value (Metric)	Unit	Test Method
UL Flame Rating	V0 – 2 mm	-	UL-94
LOI	30	%	ASTM D-2863
Smoke Density (0.75 mm)	TBD	Flaming DM Non flaming DM	ASTM E662

Material Preparation

- Prior to processing, **ESTANE® ZHF 95AP7 NAT 01** must be dried at 100°C for 4 hours.
- It is recommended to dry the material in a vacuum or dehumidifying type dryer. Target dew point should be -40°C.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2021 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>

- **ESTANE® ZHF 95AP7 NAT 01** can be processed on any conventional extruder:

Recommended EXTRUSION Temperature Profile:

	°C
Zone 1	205-210
Zone 2	205-210
Zone 3	205-210
Zone 4	210-215
Adapter (5)	210-215
Die Zone 1 (6)	210-215
Die Zone 2	210-215
Target Melt Temperature	195-200
Target RPM	20-40

In case of need, please contact our Technical Service Department.

Storage

ESTANE® ZHF 95AP7 NAT 01 must be stored in a cool (15-25°C) and dry place. Standard Practice of consuming resin first-in first-out basis should be employed. Contact your account manager for specific information related to shelf life.

For further information refer to Lubrizol Advanced Materials processing guides.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2021 The Lubrizol Corporation.
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>