

Technical Data Sheet
Type: Polycaprolactone Thermoplastic Polyurethane (TPU)

Features: High clarity and printed part quality

Uses: 3D Printing using Fused Filament Fabrication (FFF) technology

Physical Properties	Value (Metric)	Unit	Test Method
Hardness (5 sec)	98	Shore A	ISO 868
Specific Gravity	1.09	g/cm3	ISO 2781
Tensile Strength (XY)	28	MPa	ISO 527
Ultimate Elongation (XY)	380	%	ISO 527
Tensile Stress at (XY):			
- 100 % Elongation	13	MPa	ISO 527
- 300 % Elongation	23	MPa	ISO 527

- Filament dried at 70°C during 2h in a convection oven prior to printing
- Printing conditions: MakerBot Replicator, extrusion temp = 230C, base = 110C, speed = 90mm/s
- Prior to testing samples were conditioned at 23°C for 48 hours.

Supply Form and Standard Packaging

- **ESTANE® 3D TPU F98A-030 CR HC PL** is supplied in pellet form and packaged in 25kg bags.

Material Preparation

- Prior to strand extrusion, **ESTANE® 3D TPU F98A-030 CR HC PL** pellets must be dried at **100°C** for 2-4 hours.
- It is recommended to dry the pellets in a desiccant type dryer. Target dew point should be **-40°C**.
- The produced filaments must be kept in a sealed bag with enough silica gel desiccant until use, in moisture free conditions during printing, and dried overnight at 70C in a standard convection oven in case of moisture exposure
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.


<http://go.lubrizol.com/EP>

Recommended Strand Extrusion Conditions:

- ESTANE® 3D TPU F98A-030 CR HC PL can be processed on any conventional extruder.

	°C
Zone 1	200
Zone 2	210
Zone 3	215
Zone 4	220
Die	220

For further information refer to Lubrizol Advanced Materials processing guides.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



<http://go.lubrizol.com/EP>