

Technical Data Sheet

Type: ESTANE® R195A is aromatic, polyether-based thermoplastic polyurethane (TPU).

Features: Excellent physical properties, low temperature performance and clarity with a wide processing window for extrusion.

Uses: Blown and flat die/cast film extrusion. Injection and blow molding.

Physical Properties	Standard No.	Units	Value
Hardness	ASTM D792	Shore A	95
Specific Gravity	ASTM D2240		1.14
Mechanical			
Tensile Strength	ASTM D412	psi (MPa)	9250 (64)
Ultimate Elongation	ASTM D412	%	435
Tensile Stress:			
At 100% elongation	ASTM D412	psi (MPa)	1600 (11)
At 300% elongation	ASTM D412	psi (MPa)	4500 (31)
Tear Strength			
Graves	ASTM D624 (die C)	lb/in (kg/mm)	680 (12.1)
Trouser	ASTM D470	lb/in (kg/mm)	180 (3.1)
Taber Loss (1000 rev)	ASTM D3389 (H18, 1000g)	Oz (mg)	0.0012 (34)
Tm (by DSC)	Lubrizol	°F(°C)	349 (176)
Tg (by DSC)	Lubrizol	°F(°C)	-51 (-46)

- Prior to testing samples were conditioned at 23 °C for 48 hours.
- Based on extruded sheet (30 mils)
- Listed values are "typical (average) values" and should/cannot be applied for specification purposes.

Supply Form and Standard Packaging

- ESTANE R195A TPU is supplied in pellet form and packaged in 50 lb bags or 1000 lb boxes.

Material Preparation

- Prior to processing, ESTANE R195A TPU must be dried at 220°F (104°C) for 2-4 hours.
- It is recommended to dry the material in a desiccant type dryer. Target dew point should be -40°C.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

The Lubrizol Corporation ("Lubrizol") hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.



Processing Conditions

Estane R195A TPU can be processed on any conventional extruder.

Injection Conditions

	F/°C°
Zone 1	350/177
Zone 2	360/182
Zone 3	370/188
Zone 4	380/193
Adapter (5)	390/199
Die Zone 1(6)	390/199
Die Zone 2	390/199

Melt Temp. Mid-Range: 385°F/196°C
Screen Pack Recommendation: 20/40/80

Application Information: Polyether TPU for High Performance Film/Sheet

Application Properties	Value	Unit	Test Method
Tensile Set (200% Elongation)	13	%	ASTM D412
Kofler Melt Point	336 (169)	°F/°C	Lubrizol
Volume Swell in Water (24h/23C)	0.5	%	ASTM D471

¹ For use in repeat applications

For further information refer to Lubrizol processing guides.

The Lubrizol Corporation ("Lubrizol") hopes that you have found the information provided helpful, but you are cautioned that this material, including any prototype formulas, is for informational purposes only and you are solely responsible for making your own assessment of appropriate use of the information. TO THE MAXIMUM EXTENT PERMITTED BY APPLICABLE LAWS, LUBRIZOL MAKES NO REPRESENTATIONS, GUARANTEES, OR WARRANTIES (WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE), INCLUDING ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR REGARDING THE COMPLETENESS, ACCURACY, OR TIMELINESS OF ANY INFORMATION. Lubrizol does not guarantee how the materials referenced herein will perform in combination with other substances, in any methods, conditions, or processes, with any equipment, or in non-laboratory environments. BEFORE COMMERCIALIZATION OF ANY PRODUCT CONTAINING THESE MATERIALS, YOU SHOULD THOROUGHLY TEST SUCH PRODUCT, INCLUDING HOW THE PRODUCT IS PACKAGED, TO DETERMINE ITS PERFORMANCE, EFFICACY, AND SAFETY. You are solely responsible for the performance, efficacy, and safety of any products you manufacture. Lubrizol shall not be liable, and you shall assume all risk and responsibility for, any use or handling of any material. Any claims may not be approved in all jurisdictions. Any entity making claims related to these products is responsible for complying with local laws and regulations. Nothing contained herein is to be considered as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner, and it is your sole responsibility to determine if any issues related to patent infringement of any component or combination of components relating to the information provided exists. You acknowledge and agree that you are using the information provided herein at your own risk. If you are dissatisfied with the information provided by Lubrizol, your exclusive remedy shall be to not use the information.

