

**Technical Data Sheet**

**Type:** ESTANE® ZHF 58202 NAT 02 is a non-halogen, flame retardant, aromatic polyether-based thermoplastic polyurethane (TPU).

**Application:** Extrusion

Physical Properties	Value (Metric)	Unit	Test Method
Hardness	A/1:89	Sh. A	ISO 868
Specific Gravity	1.23	g/cm <sup>3</sup>	ISO 2781
Tensile Strength	28	MPa	ISO 527
Elongation @ break	600	%	ISO 527
Tensile Stress at:			
Modulus @ 100%	8	MPa	ISO 527
Modulus @ 300%	10	MPa	ISO 527
Abrasion Loss	65	mm <sup>3</sup>	ISO 4649-A
Tear Strength nicked	59	kN/m	ISO 34-1B

- Based on extruded strips.
- Prior to testing samples were conditioned at 23°C for 48 hours
- Listed values are “typical (average) values” and should/cannot be applied for specification purposes.

Application Specific Properties	Value (Metric)	Unit	Test Method
UL Flame Rating	V2-2mm	-	UL-94
LOI	25	%	ASTM D-2863
UL Temperature rating	105	°C	UL-1581
Smoke Density (0.75 mm)	DS @4:106 DS @4: 8	Flaming DM Non flaming DM	ASTM E662

**Material Preparation**

- Prior to processing, ESTANE® ZHF 58202 NAT 02 must be dried at 100°C for 4 hours.
- It is recommended to dry the material in a dehumidifying type dryer. Target dew point should be **-40°C**.
- Depending on the applied processing technique, the maximum moisture level should be 0.02%.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.



- ESTANE® ZHF 58202 NAT 02 can be processed on any conventional extruder.

**Recommended EXTRUSION Temperature Profile:**

	°C
<b>Zone 1</b>	<b>150-160</b>
<b>Zone 2</b>	<b>155-165</b>
<b>Zone 3</b>	<b>160-170</b>
<b>Zone 4</b>	<b>165-175</b>
<b>Adapter (5)</b>	<b>165-175</b>
<b>Die Zone 1 (6)</b>	<b>165-175</b>
<b>Die Zone 2</b>	<b>165-175</b>
<b>Target Melt Temperature</b>	<b>155-165</b>
<b>Target RPM</b>	<b>20-40</b>

In case of need, please contact our Technical Service Department.

**Storage**

**ESTANE® ZHF 58202 NAT 02** must be stored in a cool (15-25°C) and dry place. Standard Practice of consuming resin first-in first-out basis should be employed. Contact your account manager for specific information related to shelf life.

**For further information refer to Lubrizol Advanced Materials processing guides.**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

© 2021 The Lubrizol Corporation.  
All rights reserved. All marks are the property of The Lubrizol Corporation.



<http://go.lubrizol.com/EP>