

**Technical Data Sheet**
**Type:** Estane® 2103-90AE is a thermoplastic polyurethane elastomer.

Properties	Test Method	English		S.I.	
		Values <sup>†</sup>	Units	Values <sup>†</sup>	Units
<b>Physical<sup>(1)</sup></b>					
Shore Hardness	ASTM D 2240	90 47	A D	90 47	A D
Specific Gravity	ASTM D 792	1.14		1.14	
Melt Flow Rate, 224°C/8700g	ASTM D 1238	-	g/10min	7	g/10min
Taber Abrasion, Wt Loss, 1000g wt 1-1000g, H-22 (coarser)	ASTM D 1044	-	mg	50	mg
Mold Shrinkage, Transverse direction	ATSM D 955	0.4-0.6	%	0.4-0.6	%
Mold Shrinkage, Flow direction	ATSM D 955	0.5-0.7	%	0.5-0.7	%
<b>Mechanical<sup>(2)</sup></b>					
Tensile Modulus -50% elongation -100% elongation -300% elongation	ASTM D 412	920 1400 2600	psi psi psi	6.3 9.7 17.9	MPa MPa Mpa
Ultimate Elongation	ASTM D 412	530	%	530	%
Ultimate Tensile Strength	ASTM D 412	5540	psi	38.2	Mpa
Elongation Set After Break	ASTM D 412	60	%	60	%
Tear Strength, Die C	ASTM D 624	760	PLI	133	KN/m
Compression Set, Method B -22 hrs @ 25°C -22 hrs @ 70°C	ASTM D 395	25 40	% %	25 40	% %
Flexural Modulus	ATSM D 790	10,000	psi	65.9	MPa
<b>Thermal</b>					
Vicat Softening Point (120°C/hr, 9.8N)	ASTM D 1525	195	°F	90.6	°C
Glass Transition Temperature	DSC	-29	°F	-34	°C
CLTE, in-flow	ASTM D 696	86.1	in/in/°F	155	mm/mm/°C
<b>Processing Conditions (Typical)</b>					
Drying Temperature (air dew point <-40C)		190-220	°F	88-104	°C
Melt Temperature (Molding)		380-410	°F	193-210	°C
Mold Temperature		370-400	°F	188-204	°C

<sup>†</sup>Typical properties; not to be construed as sales specifications. Fabrication conditions, part design, additives, processing aids, finishing materials and use conditions can all affect the integrity, performance and regulatory status of finished goods.

<sup>2</sup>Tests conducted on 0.126 inch (3.2mm) injection molded specimen, unannealed, unless noted.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information often is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance or reproducibility. Formulations presented may not have been tested for stability and should be used only as a suggested starting point. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability for any use or handling of any material beyond Lubrizol Advanced Materials, Inc.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation nor as an inducement to practice any patented invention without permission of the patent owner.

